



www.btm.co

Bituminous Waterproofing Membranes Co.
Kemalpaşa Org. San. Bölgesi Mah. Gazi Bulvarı. No:
152 Kemalpaşa / İZMİR / TURKEY
Tel:+90 0232 877 04 02 (8 line)
Fax: +90 0232 877 04 10

PRODUCT DATA SHEET



ETA 17/0341

SHINGLE GALAXY MODERN (RUBY)

Document number :PDS-102-1

Publication Date : 05th,Jan.2011 Revision date : 05th,Feb.2018

PRODUCT DESCRIPTION	Bitumen shingles with mineral and synthetic reinforcements			
PRODUCT COMPOSITION	Reinforcement: Type 4- Glass non woven with or without longitudinal reinforcement by films or grid Coating Type : Tip X- Oxidized bitumen Mineral: Type 2- Mineral Granules			
USAGE	Used for waterproofing of pitched roofs and/or wall cladding.			
APPLICATION METHOD	Joined by self-adhesive part. Please refer to application booklet.			
TOP SURFACE	Coloured mineral			
BOTTOM SURFACE	Siliconized film			
STORAGE	Keep the bundles from direct sunlight			
ECOLOGICAL DATA	Can be used in natural atmosphere			
TEST	METHOD	UNIT	TOLERANCE	VALUES
Width	TS EN 544	mm	±3	1000
Height	TS EN 544	mm	±3	320
Tensile Strength (Longitudinal)	EAD 22020-00-0402-2.2.10.1	N/5 cm	Min.	600
Tensile Strength (Transverse)	EAD 22020-00-0402-2.2.10.2	N/5 cm	Min.	400
Nail Shank Tear resistance (Transverse)	EAD 22020-00-0402-2.2.10.3	N	Min.	100
Water Absorption	EAD 22020-00-0402-2.2.7.3	%	Max.	2
Resistance to UV radiation	EAD 22020-00-0402-2.2.11.1	-	-	PASS
Resistance to UV blistering	EAD 22020-00-0402-2.2.8	-	-	PASS
Flow resistance at elevated temperature	EAD 22020-00-0402-2.2.7.1	mm	Max.	2
Adhesion of mineral granuls	TS EN 12039	gr	Max.	2,5
Reaction to fire	TS EN 13501-1	-	-	E
External fire performance	TS ENV 1187- TS EN 13501-5	-	-	Broof
Watertightness (Weight of Bitumen)	EAD 22020-00-0402-2.2.6.1	gr/m ²	±150	995

NPD = (No performance defined)

* For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet

The manufacturer serves the right to modify, at any time, the characteristics of its products

BF/14-17-0